



ECR GLASSFLAKE UNMILLED Grade GF350nm

Technical Information

Extra Corrosion Resistant Glassflake is manufactured from a modified C glass

Chemical Analysis

SiO ₂	=	64 - 70%
K ₂ O	=	0 - 3%
B ₂ O ₃	=	2 - 5%
ZnO	=	1 - 5%
Na ₂ O	=	8 - 13%
MgO	=	1 - 4%
CaO	=	3 - 7%
Al ₂ O ₃	=	3 - 6%
TiO ₂	=	0 - 3%

Glass composition may vary slightly from batch to batch

Physical Properties

Apparent Density (H ₂ O=1)	0.015
Real Density (H ₂ O=1)	2.60
Softening Temperature DIM 52324	688°C
Melt Temperature (molten - flow)	930 - 1020°C
Refractive Index	1.52

Particle Size Distribution

1700-150µm	80% or more
<150µm	20% or less

Thickness

The nominal thickness of the glass is ca.350nm

Surface coatings

Glassflake materials are offered with the option of surface pre-treatment with a range of silane silane coupling agents which are listed below;

- 3-Aminopropyltriethoxy Silane
- Vinyl trimethoxy Silane
- γ-Glycidoxypropyltrimethoxy Silane
- Methacryloxypropyltrimethoxy Silane

Packaging

GF350nm is packed in 2.5kg (net.) anti-static, antislip, heat sealed PE sacks
Bulk shipments are further packed in pallet boxes containing 15 sacks (37.5kg net.)
Pallet box dimensions are 1200 x 1100 x 800mm

Should further information regarding this product be required, please consult Glassflake Technical Services.

Glassflake Ltd
Forster Street Leeds LS10 1PW England
info@glassflake.com www.glassflake.com