

ECR GLASSFLAKE MILLED Grade GF750nmM



Technical Information

Extra Corrosion Resistant Glassflake is manufactured from a modified C glass

Chemical Analysis

SiO ₂	=	64 - 70%
K ₂ O	=	0 - 3%
B ₂ O ₃	=	2 - 5%
ZnO	=	1 - 5%
Na ₂ O	=	8 - 13%
MgO	=	1 - 4%
CaO	=	3 - 7%
Al ₂ O ₃	=	3 - 6%
TiO ₂	=	0 - 3%

Glass composition may vary slightly from batch to batch

Physical Properties

Apparent Density (H ₂ O=1)	0.06
Real Density (H ₂ O=1)	2.60
Softening Temperature DIM 52324	688 ^o C
Melt Temperature (molten - flow)	930 - 1020 ^o C
Refractive Index	1.52

Particle Size Distribution

1000 - 300µm	10% or less
300 - 50µm	65% or more
<50µm	25% or less

Thickness

The thickness of the glass is ca.750nm

Surface coatings

Glassflake materials are offered with the option of surface pre-treatment with a range of silane silane coupling agents, listed below :

3-Aminopropyltriethoxy Silane
Vinyl trimethoxy Silane
γ-Glycidoxypropyltrimethoxy Silane
Methacryloxypropyltrimethoxy Silane

Packaging

GF750nmM is packed in 7.5kg (net.) anti-static, antislip, heat sealed PE sacks
Bulk shipments are further packed in pallet boxes containing 15 sacks (112.5kg net.)
Pallet box dimensions are 1200 x 1100 x 800mm

Glassflake Ltd., Stafford Street, Off Hunslet Road, Leeds. LS10 1PW
Tel: +44 (0) 113 2703615 Fax: +44 (0) 113 2718750
www.glassflake.com