

GLASSFLAKE AgFlake



AgFlake 2030

Product Code: GFEAGF-2030

Technical Information

AgFlake functional conductive pigments are based on our thin borosilicate glass flakes which have an average thickness of 2 microns and are coated with high loadings of silver for improved conductivity and shielding properties.

Composition					
Ingredients	Composition	By Weight (%)		CAS No.	CI No.
Calcium Sodium Borosilicate	Glass	68 - 72		65997-17-3	-
Silver	Ag	28 - 32		7440-22-4	77820
Tin Oxide	SnO ₂	<0.5		18282-10-5	77861
Nominal flake thickness (µm):	Uncoated	2.0		Coated	2.0- 2.5
Particle Size Diameter (µm):	D50	Average 20		(By Malvern Mastersizer 2000S)	
Oil Absorption (g/100g):	Range	80	100	ASTM D281-12	
pH:	7.0 - 11.0		(10% Aqueous Suspension)		
Loss on Drying:	<3% max				
Powder volume resistivity @	9.4x10 ⁻¹				
Trace Elements - Typical: (Glassflake Substrate)	Mercury (Hg)	2 ppm max		IEC 62321:2008 ICP-MS	
	Arsenic (As)	5 ppm max			
	Lead (Pb)	5 ppm max			
	Cadmium (Cd)	2 ppm max			
	Total Barium (Ba)	50 ppm max			
	Antimony (Sb)	2 ppm max			
	Total Chromium (Cr)	15 ppm max			
	Nickel (Ni)	5 ppm max			
Microorganisms:	100 CFU/g max			No Pathogens	

Glassflake Ltd
 Donisthorpe Street Leeds LS10 1PL England
 info@moonshinepigments.com www.moonshinepigments.com

This information is given in good faith without guarantee or liability. All values are approximate.