

# GLASSFLAKE AgFlake



## AgFlake 4035

Product Code: GFEAGF-4035

## Technical Information

AgFlake functional conductive pigments are based on our thin borosilicate glass flakes which have an average thickness of 2 microns and are coated with high loadings of silver for improved conductivity and shielding properties.

Composition				
Ingredients	Composition	By Weight (%)	CAS No.	CI No.
Calcium Sodium Borosilicate	Glass	63 - 67	65997-17-3	-
Silver	Ag	33 - 37	7440-22-4	77820
Tin Oxide	SnO <sub>2</sub>	<0.5	18282-10-5	77861
Nominal flake thickness (µm):	Uncoated	2.0	Coated	2.0- 2.5
Particle Size Diameter (µm):	D50	Average 40	(By Malvern Mastersizer 2000S)	
Oil Absorption (g/100g):	Range	76 95	ASTM D281-12	
pH:	7.0 - 11.0		(10% Aqueous Suspension)	
Loss on Drying:	<3% max			
Powder volume resistivity @	4.8x10 <sup>-1</sup>			
Trace Elements - Typical: (Glassflake Substrate)	Mercury (Hg)	2 ppm max		IEC 62321:2008 ICP-MS
	Arsenic (As)	5 ppm max		
	Lead (Pb)	5 ppm max		
	Cadmium (Cd)	2 ppm max		
	Total Barium (Ba)	50 ppm max		
	Antimony (Sb)	2 ppm max		
	Total Chromium (Cr)	15 ppm max		
	Nickel (Ni)	5 ppm max		
Microorganisms:	100 CFU/g max		No Pathogens	

Glassflake Ltd  
Donisthorpe Street Leeds LS10 1PL England  
info@moonshinepigments.com www.moonshinepigments.com

This information is given in good faith without guarantee or liability. All values are approximate.