



# ECR GLASSFLAKE UNMILLED Grade GF750nm

## Technical Information

Extra Corrosion Resistant glassflake, manufactured from a modified C glass.

### Chemical Analysis

SiO <sub>2</sub>	=	64 - 70%
K <sub>2</sub> O	=	0 - 3%
B <sub>2</sub> O <sub>3</sub>	=	2 - 5%
ZnO	=	1 - 5%
Na <sub>2</sub> O	=	8 - 13%
MgO	=	1 - 4%
CaO	=	3 - 7%
Al <sub>2</sub> O <sub>3</sub>	=	3 - 6%
TiO <sub>2</sub>	=	0 - 3%

### Physical Properties

Apparent Density (H <sub>2</sub> O=1)	0.03
Real Density (H <sub>2</sub> O=1)	2.60
Softening Temperature DIM 52324	688°C
Melt Temperature (molten - flow)	930 - 1020°C
Refractive Index	1.52

Glass composition may vary slightly from batch to batch

### Particle Size Distribution

By Malvern Mastersizer 2000  
D50 = 140-160um

### Thickness

The nominal thickness of the glass is ca. 750nm

### Surface coatings

Glassflake materials are offered with the option of surface pre-treatment from the following range of silane coupling agents;

- 3-Aminopropyltriethoxy Silane (Amino)
- Vinyl trimethoxy Silane (Vinyl)
- γ-Glycidoxypropyltrimethoxy Silane (Epoxy)
- Methacryloxypropyltrimethoxy Silane (Acrylic)

### Packaging

GF750nm is packed in 50kg (net.) box liner

Bulk shipments are further packed in pallet boxes containing 1 sack (50kg net.)  
Pallet box dimensions are 1200 x 1100 x 800mm

Glassflake LTD  
Donisthorpe Street, Leeds, LS10 1PL, England  
info@glassflake.com www.glassflake.com