



ECR GLASSFLAKE MILLED Grade GF750nmM Nanoflake™

Technical Information

Extra Corrosion Resistant glassflake, manufactured from a modified C glass.

Chemical Analysis

SiO ₂	=	64 - 70%
K ₂ O	=	0 - 3%
B ₂ O ₃	=	2 - 5%
ZnO	=	1 - 5%
Na ₂ O	=	8 - 13%
MgO	=	1 - 4%
CaO	=	3 - 7%
Al ₂ O ₃	=	3 - 6%
TiO ₂	=	0 - 3%

Physical Properties

Apparent Density (H ₂ O=1)	0.06
Real Density (H ₂ O=1)	2.60
Softening Temperature DIM 52324	688°C
Melt Temperature (molten - flow)	930 - 1020°C
Refractive Index	1.52

Glass composition may vary slightly from batch to batch

Particle Size Distribution

By Malvern Mastersizer 2000
D50 = 105 – 130 µm

Thickness

The nominal thickness of the glass is ca.750nm

Surface coatings

Glassflake materials are offered with the option of surface pre-treatment from the following range of silane coupling agents which are listed below;

- 3-Aminopropyltriethoxy Silane (Amino)
- Vinyl trimethoxy Silane (Vinyl)
- γ-Glycidoxypropyltrimethoxy Silane (Epoxy)
- Methacryloxypropyltrimethoxy Silane (Acrylic)

Packaging

GF750nmM is packed in 100kg (net.) anti-static, antislip, heat sealed PE sacks
Bulk shipments are further packed in pallet boxes containing 1 sack (100kg net.) Pallet
box dimensions are 1200 x 1100 x 800mm

Should further information regarding this product be required, please consult Glassflake Technical Services.

Glassflake Ltd
Donisthorpe Street, Leeds, LS10 1PL, England
info@glassflake.com www.glassflake.com